

Versaperm Limited Incorporating G W Cheel Scientific Instruments

Permeability Laboratory Report

Customer:	Specialist Technical Products			Mike Summers	Our Ref		ST1571	
Sample number	Type	Identification	Thickness /mm	Test Conditions		Measurement Time /days	Water Vapour Permeability/ g/m ² day	Water Vapour Permeability/ g.mm/m ² day
				Temp / °C	Humidity /%RH			
1	Sheet	HQB1	2.00	25	75	7	0.012	0.025
2	Sheet	HQB1T	2.00	25	75	7	0.001	0.003
3	Sheet	HQB2	1.70	25	75	7	0.006	0.010
COMMENTS Tested according to BS15106-3					Tested By	C A Roberts		
					Date	17/12/2012		
					Report No	ST1571		
					Sheet	1 of 1		